



ALT-210 Roof Coating
Non-Fibered Emulsion Roof Coating

GENERAL: ALT-210 Roof Coating is a general purpose non-fibered emulsion roof coating prepared from an asphalt binder, carefully refined and emulsified in water by means of selected colloids. The asphalt emulsion thus produced is of heavy paint consistency. ALT-210 Roof Coating is a tough, flexible black-asphalt compound especially designed to provide excellent protection to most roof surfaces against weathering. ALT-210 Roof Coating will not burn or support combustion in a liquid state. It has no odor or fumes, and resists the absorption of exterior moisture:

SURFACE

PREPARATION: All surfaces should be clean and free from oil, grease, rust, dirt and other foreign matter. Excess water should be removed, if possible, before application of ALT-210 Roof Coating.

APPLICATION: ALT-210 Roof Coating is easily applied by brush, roller, or spray equipment.
Brush Application: Apply with a wide fiber brush at the rate of 3 to 4 gallons per 100 sq. ft.
Spray Application: Utilize a standard heavy duty spray pump using heavy duty guns and nozzles. Apply at the rate of 3 to 4 gallons per 100 sq. ft. Equipment manufacturer should be consulted for more complete information.

COVERAGE: Apply at the rate of 3 to 4 gallons per 100 sq. ft.

CAUTION: Do not apply when rain is imminent. **Protect from freezing.** Coating must be dried before exposure to water. Store in a heated room and keep container covered when not in use. Keep out of reach of children. **Do not thin.** Avoid prolonged contact with skin. Dispose of in an environmentally safe manner.

COLD-PROCESS SYSTEMS AND COATINGS, EITHER EMULSION OR SOLVENT BASED, SHOULD ONLY BE INSTALLED ON DECKS WITH POSITIVE DRAINAGE.

PER NRCA, (NATIONAL ROOFING CONTRACTORS ASSOCIATION) "THE CRITERIA FOR JUDGING PROPER SLOPE FOR DRAINAGE IS THAT THERE BE NO EVIDENCE OF STANDING WATER ON THE DECK 48 HOURS AFTER IT STOPS RAINING."

PACKAGING: Bulk, 275 gallon totes, 55 gallon drums, and 5 gallon pails

Material Specifications:

Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs)	9.20 ± 9.40
Solids by Weight	53 ± 2%
Solids by Volume	8%
Color.....	Brown Wet-Black Dry
Permeability	0.5 Metric Perms
Dry Time.....	4 to 6 Hours
Service Temperature Range:	-40°F to 180°F