



Allstates Coatings Co.®

100 N. Lee Drive • Gladewater, TX 75647
903-845-6436 • www.allstatescoatings.com

PRODUCT INFORMATION

ALT-215 Pipe Cote



WATER QUALITY

< MH63054 >

ALT-215 Pipe Cote

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.



**Certified to
NSF/ANSI 61**

GENERAL: A non-flammable rubber modified asphalt emulsion modified with polymer and plasticizers to achieve excellent adherence to the substrate. Pipe Cote is a black one component, sprayable or dipped coating specially designed to protect from corrosion, water and environmental elements for prime or top coat on any surface-metal, concrete, wood or brick.

PREPARATION: Surface must be dry, free from dirt, dust and oil. If necessary, dirt, loose pieces of coatings or chemical residue should be removed. DO NOT use when surface is wet or when temperatures are below 40°F (4.4°C). **CAUTION:** Wear adequate eye protection and breathing apparatus during cleaning and coating procedure.

APPLICATION: Mix Pipe Cote before using. No thinning is necessary. Apply by dipping or with adequate spray or other appropriate equipment. NSF Certified/UL Classified - Maximum 4 mils DFT, 96 hours cure at 77°F (25°C). For interior application plenty of ventilation and fresh air is required.

COVERAGE: For estimation use 645 - 900+ (depending upon nonvolatile %) sq. feet per gallon (1 mil dry film)

CAUTION: KEEP FROM FREEZING. DO NOT store in direct sunlight or where temperatures exceed 100°F (37.8°C). Container should be closed when not in use. Keep out of the reach of children. Wash tools in water. Use paint thinner if material has dried.

PACKAGING: 5 gallon pails, 55 gallon drums, 275/330 gallon tote tanks and bulk.

Material Specifications:

Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs)	8.30 - 9.70
Nonvolatile %, ASTM D2939	40.00 - 58.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit)	58 - 68 KU
Softening Point (0°F), ASTM D36.....	200
Penetration (0.1 mm), ASTM D5.....	30
V.O.C. as supplied (lbs per gallon).....	0.00 - 0.06
Std. Spec. for Emulsified Asphalt	
AASHTO Designation M140-70	meets spec.
ASTM Designation D977-73	meets spec.
Salt Fog, ASTM B117; 2ml/hr (FIRST appearance of rust). 198 hrs, no blistering, no loss of	adhesion or re-emulsification
Resistance to water, ASTM D2939.....	no blistering, no loss of adhesion, no re-emulsification
Dry Time (mins) ASTM D2939 @ 5 mil wet	10
Shelf Life (yrs).....	6 months

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. Only products bearing the NSF and/or UL Mark on the product, product packaging, and/or documentation shipped with the product are Certified/Classified. Published technical data and instructions are subject to change without notice. Contact your Allstates Coatings representative for additional technical data and instruction