



Fast-Dry Acrylic Waterborne Traffic Paint TT-P-1952B

Available Colors: ALT-632 White, ALT-633 Yellow, ALT-634 Blue, ALT-628 Red,
ALT-631 Black

GENERAL: Fast-Dry waterborne striping paints formulated with 100% acrylic polymer emulsions of superior quality that are exceptionally tough durable, and attractive. It is suitable for application on surfaces such as concrete, bituminous, asphalt, tar and previously painted areas. It is ready to use on parking lots, traffic islands, walkways, aisles, fire lanes, safety areas, and related surfaces such as airport runways, roadways and highways.

SURFACE

PREPARATION: Surface must be clean-free from dirt and oil. It is necessary to etch concrete surfaces.

APPLICATION: Mix well before using. If applied by spray, strain. For brush or roller, use as is. Lower the temperature and higher the humidity, extended drying time may be required. It can be reflectorized by using the drop-on type Glass Beads.

COVERAGE: 400 to 450 linear feet of 4" stripe per gallon. (@ 12.0 mil. wet film).

CAUTION: **KEEP FROM FREEZING.** Do not stripe when rain is in forecast, on wet surfaces, or when temperature is below 45°F. Wash tools in water. Use a suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Because of alkali inherent in concrete surfaces there is no product guarantee on these. Keep out of the reach of children.

PACKAGING: 5 gallon pails, 55 gallon drums and 250 or 275 gallon totes.

Material Specifications:

Requirements:

Weight per Gallon @ 77°F, ASTM D1475, (lbs)	13.30 - 14.00
Viscosity @ 77°F, (Kreb's Stormer Unit) for ambient application.....	75 – 80 KU
for heat application.....	85 – 100 KU
% Weight solids.....	74.00 ± 2.00
% Volume Solids	58.00 ± 2.00
Dry Time (15 mil. - wet)	
@ 77°F & 50% R.H. Dry to no pick-up	17-20 min
VOC, grams/liter	150
Dry opacity, White & colors	0.92
Fineness of dispersion, Hegman.....	3.0
Directional reflectance of white paint, %.....	85
Bleeding ratio	0.95

* Can be heated to 110°F to 130°F to accelerate curing time therefore allowing the work area to be back in service sooner.

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. Published technical data and instructions are subject to change without notice. Contact your Allstates Coatings representative for additional technical data and instruction.