



# Allstates Coatings Co.<sup>®</sup>

100 N. Lee Drive • Gladewater, TX 75647  
903-845-6436 • [www.allstatescoatings.com](http://www.allstatescoatings.com)

## PRODUCT INFORMATION

### ALT-650 Tack-Cote

#### ALT-650 Tack-Cote

Rejuvenates and Promotes Adhesion

**GENERAL:** An **SS-1h** asphaltic emulsion based Tack-Cote is specially designed for prime or tack cote on any oxidized asphaltic surfaces, alligated areas, bird baths, pot holes, or for patching and filling cracks to promote adhesion and rejuvenate asphaltic surfaces.

#### SURFACE

**PREPARATION:** Surface must be dry, clean and free from all loose material, dirt and dust.

**APPLICATION:** Mix well before using. Tack-Cote can be applied with any suitable machine, pushbroom, mop, or squeegee. Tack-Cote will set under good conditions within 30 minutes, depending on weather conditions and coating thickness. Do not use when rain is forecast, when surface is wet or when temperature is below 50°F.

**COVERAGE:** Depending on type of application and job specification. For details on specific use, check with manufacturers. (For estimation purpose only: 500 Ft<sup>2</sup> per gallon.)

**COLOR:** Jet black upon drying.

**CAUTION:** **KEEP FROM FREEZING.** Wash tools in water. Use a paint thinner if material has dried. Do not store in direct sunlight or where temperature exceeds 100°F. Container should be closed when not in use. Keep out of the reach of children. Exterior use only.

**PACKAGING:** 5 gallon pails, 55 gallon drums and 275 gallon totes or bulk

#### Material Specifications:

#### Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs) .....	8.30 - 8.50
Nonvolatile %, ASTM D2939 .....	65.0
Resistance to water, ASTM D2929 .....	no loss of adhesion, no re-emulsification
Viscosity @ 77°F, ASTM D 562 (Kreb's Stormer Unit).....	55 - 60 KU
Penetration (0.1mm), ASTM D5 .....	50 - 80
Std. Spec. for Emulsified Asphalt	
AASHTO Designation M 140-70.....	Meets spec.
ASTM Desination D 977 - 77 .....	Meets spec.
Dry Time .....	30 minutes
Flammability .....	Non-Flammable