



**Allstates Coatings Co.®**

100 N. Lee Drive ● Gladewater, TX 75647  
903-845-6436 ● www.allstatescoatings.com

**PRODUCT INFORMATION**

**ALT-670 GreyTAC Concrete Crack Filler**

**ALT – 670 GreyTAC Concrete Crack Filler**

**For Concrete Surfaces**

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

**PRODUCT DESCRIPTION**

GreyTAC Concrete Crack Filler is a uniformly blended latex emulsion which is formulated to fill cracks in horizontal concrete surfaces.

**PRODUCT USE**

GreyTAC Concrete Crack Filler is formulated to fill cracks on any horizontal concrete surface, including sidewalks, walkways, steps, patios, decks, appliance platforms, etc. There is nothing to add. Just shake the ready-to-use product and pour directly from the container. The product blends in with the natural gray color of concrete.

**SIZES**

• GreyTAC Concrete Crack Filler is available one quart (946 ml) and one gallon (3.8 L) plastic bottles.

**YIELD**

• One quart (946 ml) bottle will fill a ¼" x ½" (6 x 12 mm) crack 35' (11.6 M) long

**INSTALLATION**

**SURFACE PREPARATION**

Shake well before using. Clean all loose dirt, dust and gravel from the crack. Surfaces to receive Concrete Crack Filler should be free of oil and grease. Cleaning with an available concrete & asphalt cleaner is recommended to insure the best bond. If the crack is deeper than ¼" (6 mm), use backer rod or sand to fill the crack to within ¼" (6 mm) of the surface. Deep cracks may require more than one application due to shrinkage during curing and will have extended drying times.

**APPLICATION**

Cut the tip of the spout to make a ¼" (6 mm) to 3/8" (9 mm) hole. Squeeze Concrete Crack Seal into the crack, over-filling slightly to allow for shrinkage. A second coat can be applied after 24 hours as needed to provide a uniform finished surface.

Weight per Gallon, @ 77°F, ASTM D1010, (lbs).....13.9 – 14.5  
Viscosity @ 77°, ASTM D562 (Kreb's Stormer Unit).....100-110  
% Weight Solids.....78.0 - 81.0

**PRECAUTIONS**

• Do not apply in cracks wider than ½" (12 mm). Temperature should be between 45°F and 100°F (7°C and 38°C). Keep product from freezing. Do not apply if rain is expected within 24 hours. Do not apply to surfaces which will later be coated with anything other than acrylic water-based paint.

**WARRANTY**

Allstates Coatings Company warrants this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to Seaboard Asphalt Products Co. in writing. This limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.