



ALT – 901 Epoxy DTM Acrylic

GENERAL: EPOXY DTM Acrylic is a high performance, one component, quick drying, direct to metal acrylic finish formulated for application to a wide variety of metals and other substrates, either direct or as a UV resistant finish applied over primer. This product out performs most "DTM" systems on the market, having far superior resistance to moisture throughout the coating life. **Black color with additional colors available.**

- Corrosion, chemical and fuel resistant
- Impact and abrasion resistant
- Flash/Early rust resistant
- Salt Fog ASTM B117 10B Rated
- For metal, wood and masonry substrates
- One or two coat protection
- Low VOC and low odor

SURFACE

PREPARATION: Surface areas to be treated should be free from dirt and dust. Scrape excessive build-up of oil, grease or any other chemical stain spots. Lightly burn off excessive oil build up.

APPLICATION: Mix well before using. Normal use is full strength. Can be applied in a dip process or with a suitable spray machine, brush or roller.

COVERAGE: *Approximately 700-725 ft.² per gallon @ 1 mil dry*

CAUTION: **KEEP FROM FREEZING.** Wash tools in water. Use suitable paint thinner if material has dried. Do not store in direct sunlight. Container should be closed when not in use. Keep out of the reach of children.

PACKAGING: 5 gallon pails, 55 gallon drums and 275/330 gallon tote tanks.

NOTE: Higher solids, density and viscosity may be required for full spray application. Contact your Allstates' Representative for additional instruction.

Material Specifications:

Requirements:

Weight per Gallon, ASTM D1010, (lbs)	9.30 – 9.60
Viscosity @ 77°F ASTM D562 (Kreb's Stormer Unit).....	60 - 70 KU
% Nonvolatile by weight	48 - 51
Drying Time (min)	<10 minutes @ 3mil
Application Temp (°F).....	45°F min.
Flammability	non-flammable
V.O.C. (grams per liter).....	<70 g/l
HAPS	<1.0%

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. Published technical data and instructions are subject to change without notice. Contact your Allstates Coatings representative for additional technical data and instruction